

(19)



Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11)

**EP 1 300 430 A1**

(12)

**EUROPEAN PATENT APPLICATION**

(43) Date of publication:

**09.04.2003 Bulletin 2003/15**

(51) Int Cl.7: **C08G 61/12, C07D 333/52**

(21) Application number: **02019693.7**

(22) Date of filing: **04.09.2002**

(84) Designated Contracting States:

**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR  
IE IT LI LU MC NL PT SE SK TR**

Designated Extension States:

**AL LT LV MK RO SI**

(30) Priority: **29.09.2001 EP 01123509**

(71) Applicant: **MERCK PATENT GmbH  
64293 Darmstadt (DE)**

(72) Inventors:

- **Worrall, Christopher**  
Northwich, Cheshire, CW9 7SR (GB)
- **Heeney, Martin**  
Southampton, SO14 6TQ (GB)

- **Tierney, Steven**  
Southampton, SO15 7QW (GB)
- **Farrand, Louise**  
Blandford Forum, Dorset, DT11 9ED (GB)
- **Giles, Mark**  
Southampton, SO15 2LE (GB)
- **Thompson, Marcus**  
Hampshire, SP6 1RR (GB)
- **Shkunow, Maxim**  
Southampton SO16 6SX (GB)
- **Sparrowe, David**  
Bournemouth, Dorset, BH6 5EJ (GB)
- **McCulloch, Iain**  
Hampshire, SO20 6PE (GB)

(54) **Mono-, oligo- and polymers of benzo[b]thiophene and 2,2'-bisbenzo[b]thiophene and their use as charge transport materials**

(57) The invention relates to new conjugated mono-, oligo- and polymers of benzo[b]thiophene and bisbenzo[b]thiophene. The invention further relates to their use as semiconductors or charge transport materials in optical, electrooptical or electronic devices including field

effect transistors, electroluminescent, photovoltaic and sensor devices. The invention further relates to field effect transistors and semiconducting components comprising the new mono-, oligo- and polymers.

BEST AVAILABLE COPY

EP 1 300 430 A1

## Description

## Field of Invention

[0001] The invention relates to new conjugated mono-, oligo- and polymers of benzo[b]thiophene (thianaphthene) and bisbenzo[b]thiophene (bithianaphthene). The invention further relates to their use as semiconductors or charge transport materials in optical, electrooptical or electronic devices including field effect transistors, electroluminescent, photovoltaic and sensor devices. The invention further relates to field effect transistors and semiconducting components comprising the new mono-, oligo- and polymers.

## Background and Prior Art

[0002] Organic materials have recently shown promise as the active layer in organic based thin film transistors and organic field effect transistors [see H. E. Katz, Z. Bao and S. L. Gilat, *Acc. Chem. Res.*, 2001, **34**, 5, 359]. Such devices have potential applications in smart cards, security tags and the switching element in flat panel displays. Organic materials are envisaged to have substantial cost advantages over their silicon analogues if they can be deposited from solution, as this enables a fast, large-area fabrication route.


[0003] The performance of the device is principally based upon the charge carrier mobility of the semiconducting material and the current on/off ratio, so the ideal semiconductor should have a low conductivity in the off state, combined with a high charge carrier mobility ( $> 1 \times 10^{-3} \text{ cm}^2 \text{ V}^{-1} \text{ s}^{-1}$ ). In addition, it is important that the semiconducting material is relatively stable to oxidation i.e. it has a high ionisation potential, as oxidation leads to reduced device performance.



[0004] A known compound which has been shown to be an effective p-type semiconductor for OFETs is pentacene [see S. F. Nelson, Y. Y. Lin, D. J. Gundlach and T. N. Jackson, *Appl. Phys. Lett.*, 1998, **72**, 1854]. When deposited as a thin film by vacuum deposition, it was shown to have carrier mobilities in excess of  $1 \text{ cm}^2 \text{ V}^{-1} \text{ s}^{-1}$  with very high current on/off ratios greater than  $10^6$ . However, vacuum deposition is an expensive processing technique that is unsuitable for the fabrication of large-area films.

[0005] Regular poly(3-hexylthiophene) has been reported with charge carrier mobility between  $1 \times 10^{-5}$  and  $4.5 \times 10^{-2} \text{ cm}^2 \text{ V}^{-1} \text{ s}^{-1}$ , but with a rather low current on/off ratio between 10 and  $10^3$  [see Z. Bao et al., *Appl. Phys. Lett.* 1997, **78**, 2184]. In general, poly(3-alkylthiophenes) show improved solubility and are able to be solution processed to fabricate large area films. However, poly(3-alkylthiophenes) have relatively low ionisation potentials and are susceptible to doping in air [see H. Sirringhaus et al., *Adv. Solid State Phys.* 1999, **39**, 101].

[0006] It is the aim of the present invention to provide new materials for use as semiconductors or charge transport materials, which are easy to synthesize, have high charge mobility, good processibility and improved oxidative stability. Other aims of the invention are immediately evident to those skilled in the art from the following description.

[0007] The inventors have found that these aims can be achieved by providing new monomers, oligomers and polymers based on benzo[b]thiophene and 2,2'-bisbenzo[b]thiophene. Thus, benzo[b]thiophene (1) and 2,2'-bisbenzo[b]thiophene (2) are heterocycles that exhibit good conjugation and planarity. The introduction of alkyl chains R further improves solubility and solution processibility. Poly(2,5-benzo[b]thiophene) (3) and poly(2,2'-bisbenzo[b]thiophene) (4) exhibit a high degree of planarity in the backbone and strong interchain pi-pi-stacking interactions making them effective charge transport materials with high carrier mobilities. Also, the incorporation of alkyl substituents R leads to good solubility and thus good solution processibility of the materials according to the present invention. Solution processing during device manufacture has the advantage over vacuum deposition of being a potentially cheaper and faster technique.





[0008] The synthesis of 2,2'-bisbenzo[b]thiophene (2) has been reported by Y. Fort et al., *Tetrahedron*, 1994, 50, 41, 11893. Unsubstituted poly(benzo[b]thiophene) has been reported via an electrochemical polymerisation (J. Electroanal. Chem. 2001, 510(1-2), 29-34, Makromol. Chem. Rapid Commun., 1987, 8, 325-9). The synthesis of substituted poly(2,5-benzo[b]thiophene) has not been reported. Moreover, mono- and poly(2,2'-bisbenzo[b]thiophenes) according to the present invention have not been reported.

[0009] A further aspect of the invention relates to reactive mesogens consisting of a central core comprising one or more benzo[b]thiophene or 2,2'-bisbenzo[b]thiophene units, and optionally comprising further unsaturated organic groups that form a conjugated system together with the (bis)benzo[b]thiophene units, said core being linked, optionally via a spacer group, to one or two polymerisable groups. The reactive mesogens can induce or enhance liquid crystal phases or are liquid crystalline themselves. They can be oriented in their mesophase and the polymerisable group can be polymerised or crosslinked in situ to form polymer films with a high degree of order, thus yielding improved semiconductor materials with high stability and high charge carrier mobility.

[0010] Grell et al., *J. Korean Phys. Soc.* 2000, 36(6), 331 suggest a reactive mesogen comprising a conjugated distyrylbenzene core with two reactive acrylate end groups as a model compound for molecular electronics. However, there is no disclosure of reactive mesogens of 2,2'-bisbenzo[b]thiophene.

[0011] A further aspect of the invention relates to liquid crystal polymers, in particular liquid crystal side chain polymers obtained from the reactive mesogens according to the present invention, which are then further processed e.g. from solution as thin layers for use in semiconductor devices.

#### Definition of Terms


[0012] The terms 'liquid crystalline or mesogenic material' or 'liquid crystalline or mesogenic compound' means materials or compounds comprising one or more rod-shaped, lath-shaped or disk-shaped mesogenic groups, i.e. groups with the ability to induce liquid crystal phase behaviour. The compounds or materials comprising mesogenic groups do not necessarily have to exhibit a liquid crystal phase themselves. It is also possible that they show liquid crystal phase behaviour only in mixtures with other compounds, or when the mesogenic compounds or materials, or the mixtures thereof, are polymerised.

[0013] The term 'polymerisable' includes compounds or groups that are capable of participating in a polymerisation reaction, like radicalic or ionic chain polymerisation, polyaddition or polycondensation, and reactive compounds or reactive groups that are capable of being grafted for example by condensation or addition to a polymer backbone in a polymeranalogous reaction.

[0014] The term 'film' includes self-supporting, i.e. free-standing, films that show more or less pronounced mechanical stability and flexibility, as well as coatings or layers on a supporting substrate or between two substrates.

#### Summary of the Invention

[0015] One object of the invention are mono-, oligo- and polymers of formula I



wherein

A and C are independently of each other  $-CX^1=CX^2-$ ,  $-C\equiv C-$ , or optionally substituted arylene or heteroarylene, X<sup>1</sup> and X<sup>2</sup> are independently of each other H, F, Cl or CN,

- B is 2,5-benzo[b]thiophene or 2,2'-bisbenzo[b]thiophene that is optionally substituted with one or more groups R,
- R is H, halogen, straight chain, branched or cyclic alkyl with 1 to 20 C-atoms, which may be unsubstituted, mono- or polysubstituted by F, Cl, Br, I or CN, it being also possible for one or more non-adjacent CH<sub>2</sub> groups to be replaced, in each case independently from one another, by -O-, -S-, -NH-, -NR<sup>0</sup>-, -SiR<sup>0</sup>R<sup>00</sup>-, -SnR<sup>0</sup>R<sup>00</sup>-, -CO-, -COO-, -OCO-, -OCO-O-, -S-CO-, -CO-S-, -CH=CH- or -C≡C- in such a manner that O and/or S atoms are not linked directly to one another, optionally substituted aryl or heteroaryl, or P-Sp-X,
- R<sup>1</sup> and R<sup>2</sup> have independently of each other one of the meanings of R,
- R<sup>0</sup> and R<sup>00</sup> are independently of each other H or alkyl with 1 to 12 C-atoms,
- P is a polymerisable or reactive group,
- Sp is a spacer group or a single bond, and
- X is -O-, -S-, -OCH<sub>2</sub>-, -CH<sub>2</sub>O-, -CO-, -COO-, -OCO-, -OCO-O-, -CO-NR<sup>0</sup>-, -NR<sup>0</sup>-CO-, -OCH<sub>2</sub>-, -CH<sub>2</sub>O-, -SCH<sub>2</sub>-, CH<sub>2</sub>S-, -CH=CH-COO-, -OOC-CH=CH- or a single bond,
- a, b and c are independently of each other 0 or 1, with a + b + c > 0, and wherein in at least one recurring unit [(A)<sub>a</sub>-(B)<sub>b</sub>-(C)<sub>c</sub>] b is 1, and
- n is an integer ≥ 1,

wherein the recurring units [(A)<sub>a</sub>-(B)<sub>b</sub>-(C)<sub>c</sub>] can be identical or different, and with the proviso that in case n is 1 and a and c are 0, at least one of R, R<sup>1</sup> and R<sup>2</sup> is P-Sp-X.

**[0016]** Another object of the invention is the use of mono-, oligo- and polymers according to the invention as semiconductors or charge transport materials, in particular in optical, electrooptical or electronic devices, like for example components of integrated circuitry, field effect transistors (FET) for example as thin film transistors in flat panel display applications or for Radio Frequency Identification (RFID) tags, or in semiconducting components for organic light emitting diode (OLED) applications such as electroluminescent displays or backlights of e.g. liquid crystal displays, for photovoltaic or sensor devices, as electrode materials in batteries, as photoconductors and for electrophotographic applications like electrophotographic recording.

**[0017]** Another object of the invention is a field effect transistor, for example as a component of integrated circuitry, as a thin film transistor in flat panel display applications, or in a Radio Frequency Identification (RFID) tag, comprising one or more mono-, oligo- or polymers according to the invention.

**[0018]** Another object of the invention is a semiconducting component, for example in OLED applications like electroluminescent displays or backlights of e.g. liquid crystal displays, in photovoltaic or sensor devices, as electrode materials in batteries, as photoconductors and for electrophotographic applications, comprising one or more mono-, oligo- or polymers according to the invention.

**[0019]** Another object of the invention is a security marking or device comprising an RFID or ID tag or a FET according to the invention.

#### Detailed Description of the Invention

**[0020]** The mono-, oligo- and polymers according to the present invention are especially useful as charge transport semiconductors in that they have high carrier mobilities. Particularly preferred are mono-, oligo- and polymers wherein the group B is substituted by one or more alkyl or fluoroalkyl groups. The introduction of alkyl and fluoroalkyl side chains to the group B improves the solubility and therefore the solution processibility of the inventive materials. Furthermore, the presence of fluoroalkyl side chains also renders the inventive materials effective as n-type semiconductors. The electron-withdrawing nature of the fluoroalkyl substituents will also lower the HOMO further and result in a more stable material, which is less susceptible to oxidation.

**[0021]** Particularly preferred are mono-, oligo- and polymers comprising at least one group of formula I and at least one reactive group that is capable of a polymerisation or crosslinking reaction.

**[0022]** Further preferred are mono-, oligo- and polymers comprising at least one group of formula I that are mesogenic or liquid crystalline, in particular polymers of formula I forming calamitic phases, and reactive mesogens of formula I,

comprising one or more groups P-Sp-X, forming calamitic phases.

[0023] In the oligo- and polymers of the present invention the recurring units  $(A)_a-(B)_b-(C)_c$  in case of multiple occurrence can be selected of formula I independently of each other, so that an oligo- or polymer may comprise identical or different recurring units  $(A)_a-(B)_b-(C)_c$ . The oligo- and polymers thus include homopolymers and copolymers like for example

- statistically random copolymers, for example with a monomer sequence such as -A-B-C-C-B-A-B-,
- alternating copolymers, for example with a monomer sequence such as -A-B-C-A-B-C-, and
- block copolymers, for example with a monomer sequence such as -A-A-B-B-B-C-C-C-,


wherein the groups A and C preferably form a conjugated system together with the group B.

[0024] Further preferred are mono-, oligo- and polymers comprising one or more recurring units  $(A)_a-(B)_b-(C)_c$ , wherein  $a = c = 0$  and  $b = 1$ , very preferably consisting exclusively of such recurring units.


[0025] Further preferred are mono-, oligo- and polymers comprising one or more recurring units  $(A)_a-(B)_b-(C)_c$ , wherein  $b = c = 1$  and  $a = 0$ , very preferably consisting exclusively of such recurring units.

[0026] Further preferred are mono-, oligo- and polymers comprising one or more recurring units  $(A)_a-(B)_b-(C)_c$ , wherein  $a = b = c = 1$ , very preferably consisting exclusively of such recurring units.

[0027] Especially preferred are mono-, oligo- and polymers of formula I wherein B is selected of the following formulae



IIa



IIb

wherein  $R^3$  to  $R^{10}$  independently of each other have one of the meanings of R in formula I.


[0028] Further preferred are mono-, oligo- and polymers of formula I wherein

- n is an integer from 1 to 5000,
- n is an integer from 2 to 5000, in particular from 20 to 1000,
- n is an integer from 2 to 5,
- n is 2 and one or both of  $R^1$  and  $R^2$  denote P-Sp-X,
- n is an integer from 1 to 15 and one or both of  $R^1$  and  $R^2$  denote P-Sp-X,
- n is an integer from 2 to 5000 and  $R^1$  and  $R^2$  have one of the meanings of formula I different from P-Sp-X,
- the molecular weight is from 5000 to 100000,
- $R^3$  and/or  $R^4$  are different from H,
- $R^3$  and  $R^4$  are independently of each other selected from  $C_1$ - $C_{20}$ -alkyl that is optionally substituted with one or


more fluorine atoms, C<sub>1</sub>-C<sub>20</sub>-alkenyl, C<sub>1</sub>-C<sub>20</sub>-alkynyl, C<sub>1</sub>-C<sub>20</sub>-alkoxy, C<sub>1</sub>-C<sub>20</sub>-thioether, C<sub>1</sub>-C<sub>20</sub>-silyl, C<sub>1</sub>-C<sub>20</sub>-ester, C<sub>1</sub>-C<sub>20</sub>-amino, C<sub>1</sub>-C<sub>20</sub>-fluoroalkyl, or optionally substituted aryl or heteroaryl, in particular C<sub>1</sub>-C<sub>20</sub>-alkyl or C<sub>1</sub>-C<sub>20</sub>-fluoroalkyl,

- R<sup>3</sup> and R<sup>4</sup> are independently of each other selected from C<sub>1</sub>-C<sub>20</sub>-alkyl that is optionally substituted with one or more fluorine atoms, C<sub>1</sub>-C<sub>20</sub>-alkenyl, C<sub>1</sub>-C<sub>20</sub>-alkynyl, C<sub>1</sub>-C<sub>20</sub>-alkoxy, C<sub>1</sub>-C<sub>20</sub>-thioether, C<sub>1</sub>-C<sub>20</sub>-silyl, C<sub>1</sub>-C<sub>20</sub>-ester, C<sub>1</sub>-C<sub>20</sub>-amino, C<sub>1</sub>-C<sub>20</sub>-fluoroalkyl, or optionally substituted aryl or heteroaryl, in particular C<sub>1</sub>-C<sub>20</sub>-alkyl or C<sub>1</sub>-C<sub>20</sub>-fluoroalkyl, and R<sup>5</sup> to R<sup>10</sup> are H,
- R<sup>5</sup> to R<sup>10</sup> are independently of each other selected from C<sub>1</sub>-C<sub>20</sub>-alkyl that is optionally substituted with one or more fluorine atoms, C<sub>1</sub>-C<sub>20</sub>-alkenyl, C<sub>1</sub>-C<sub>20</sub>-alkynyl, C<sub>1</sub>-C<sub>20</sub>-alkoxy, C<sub>1</sub>-C<sub>20</sub>-thioether, C<sub>1</sub>-C<sub>20</sub>-silyl, C<sub>1</sub>-C<sub>20</sub>-ester, C<sub>1</sub>-C<sub>20</sub>-amino, C<sub>1</sub>-C<sub>20</sub>-fluoroalkyl, and optionally substituted aryl or heteroaryl,
- R<sup>1</sup> and R<sup>2</sup> are independently of each other selected from C<sub>1</sub>-C<sub>20</sub>-alkyl that is optionally substituted with one or more fluorine atoms, C<sub>1</sub>-C<sub>20</sub>-alkenyl, C<sub>1</sub>-C<sub>20</sub>-alkynyl, C<sub>1</sub>-C<sub>20</sub>-alkoxy, C<sub>1</sub>-C<sub>20</sub>-thioether, C<sub>1</sub>-C<sub>20</sub>-silyl, C<sub>1</sub>-C<sub>20</sub>-ester, C<sub>1</sub>-C<sub>20</sub>-amino, C<sub>1</sub>-C<sub>20</sub>-fluoroalkyl, and optionally substituted aryl or heteroaryl,
- A and C are optionally substituted arylene or heteroarylene,
- A and C are -CX<sup>1</sup>=CX<sup>2</sup>- or -C≡C-,
- in at least one monomer unit (A)<sub>a</sub>-(B)<sub>b</sub>-(C)<sub>c</sub> a, b and c are 1, and one of A and C is arylene or heteroarylene and the other is -CX<sup>1</sup>=CX<sup>2</sup>- or -C≡C-,
- n>1.


Especially preferred are mono-, oligo- and polymers of the following formulae







Ia







Ib




Ic









wherein  $R^1$  to  $R^{10}$  have the meanings given above, Ar is arylene or heteroarylene, and  $n$  is an integer from 1 to 5000.

**[0029]** Particularly preferred are oligo- and polymers of these preferred formulae wherein  $R^3$  and  $R^4$  are independently of each other alkyl with 1-16 C atoms that is optionally fluorinated,  $R^5$  to  $R^{10}$  are independently of each other H, F or alkyl with 1-16 C atoms that is optionally fluorinated,  $R^1$  and  $R^2$  are independently of each other H, halogen, alkyl with 1-16 C atoms that is optionally fluorinated or P-Sp-X, Ar is 1,4-phenylene, alkoxyphenylene, alkylfluorene, thiophene-2,5-diyl, thienothiophene-2,5-diyl or dithienothiophene-2,6-diyl, and  $n$  is an integer from 2 to 5000, in particular from 20 to 1000.

**[0030]** Further preferred are reactive monomers of the above preferred formulae, wherein  $n$  is 1 or 2,  $R^3$  and  $R^4$  are independently of each other alkyl with 1-16 C atoms that is optionally fluorinated,  $R^5$  to  $R^{10}$  are independently of each other H, F or alkyl with 1-16 C atoms that is optionally fluorinated,  $R^1$  and  $R^2$  are independently of each other H, halogen, alkyl with 1-16 C atoms that is optionally fluorinated or P-Sp-X, Ar is 1,4-phenylene, alkoxyphenylene, alkylfluorene, thiophene-2,5-diyl, thienothiophene-2,5-diyl or dithienothiophene-2,6-diyl, with at least one, preferably both of  $R^1$  and  $R^2$  denoting P-Sp-X.

**[0031]** Aryl and heteroaryl preferably denote a mono-, bi- or tricyclic aromatic or heteroaromatic group with up to 25 C atoms that may also comprise condensed rings and is optionally substituted with one or more groups  $R^1$  as defined in formula I.

**[0032]** Especially preferred aryl and heteroaryl groups are phenyl in which, in addition, one or more CH groups may be replaced by N, naphthalene, thiophene, thienothiophene, dithienothiophene, alkyl fluorene and oxazole, all of which can be unsubstituted, mono- or polysubstituted with L, wherein L is halogen or an alkyl, alkoxy, alkylcarbonyl or alkoxy-carbonyl group with 1 to 12 C atoms, wherein one or more H atoms may be replaced by F or Cl.

**[0033]** Arylene and heteroarylene preferably denote a bivalent mono-, bi- or tricyclic aromatic or heteroaromatic group with up to 25 C atoms that may also comprise condensed rings and is optionally substituted with one or more groups  $R^1$ .

**[0034]** Especially preferred arylene and heteroarylene groups are 1,4-phenylene in which, in addition, one or more CH groups may be replaced by N, naphthalene-2,6-diyl, thiophene-2,5-diyl, thienothiophene-2,5-diyl, dithienothiophene-2,6-diyl, alkyl fluorene and oxazole, all of which can be unsubstituted, mono- or polysubstituted with L as defined above.

**[0035]**  $CX^1=CX^2$  is preferably -CH=CH-, -CH=CF-, -CF=CH-, -CF=CF-, -CH=C(CN)- or -C(CN)=CH-.


**[0036]** If in the formulae shown above and below one of  $R^1$  to  $R^{10}$  is an alkyl or alkoxy radical, i.e. where the terminal  $CH_2$  group is replaced by -O-, this may be straight-chain or branched. It is preferably straight-chain, has 2 to 8 carbon atoms and accordingly is preferably ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, ethoxy, propoxy, butoxy, pentoxy, hexyloxy, heptoxy, or octoxy, furthermore methyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl, non-oxy, decoxy, undecoxy, dodecoxy, tridecoxy or tetradecoxy, for example.

**[0037]** Oxaalkyl, i.e. where one  $CH_2$  group is replaced by -O-, is preferably straight-chain 2-oxapropyl (=methoxymethyl), 2- (=ethoxymethyl) or 3-oxabutyl (=2-methoxyethyl), 2-, 3-, or 4-oxapentyl, 2-, 3-, 4-, or 5-oxahexyl, 2-, 3-, 4-, 5-, or 6-oxaheptyl, 2-, 3-, 4-, 5-, 6- or 7-oxaoctyl, 2-, 3-, 4-, 5-, 6-, 7- or 8-oxanonyl or 2-, 3-, 4-, 5-, 6-, 7-, 8- or 9-oxadecyl, for example.

**[0038]** Fluoroalkyl is preferably  $C_iF_{2i+1}$ , wherein  $i$  is an integer from 1 to 15, in particular  $CF_3$ ,  $C_2F_5$ ,  $C_3F_7$ ,  $C_4F_9$ ,  $C_5F_{11}$ ,  $C_6F_{13}$ ,  $C_7F_{15}$  or  $C_8F_{17}$ , very preferably  $C_6F_{13}$ .


**[0039]** Halogen is preferably F or Cl.

**[0040]** The polymerisable or reactive group P is preferably selected from  $CH_2=CW^1-COO-$ ,



CH<sub>2</sub>=CW<sup>2</sup>-(O)<sub>k1</sub>-, CH<sub>3</sub>-CH=CH-O-, HO-CW<sup>2</sup>W<sup>3</sup>-, HS-CW<sup>2</sup>W<sup>3</sup>-, HW<sup>2</sup>N-, HO-CW<sup>2</sup>W<sup>3</sup>-NH-, CH<sub>2</sub>=CW<sup>1</sup>-CO-N H-, CH<sub>2</sub>=CH-(COO)<sub>k1</sub>-Phe-(O)<sub>k2</sub>-, Phe-CH=CH-, HOOC-, OCN- and W<sup>4</sup>W<sup>5</sup>W<sup>6</sup>Si-, with W<sup>1</sup> being H, Cl, CN, phenyl or alkyl with 1 to 5 C-atoms, in particular H, Cl or CH<sub>3</sub>, W<sup>2</sup> and W<sup>3</sup> being independently of each other H or alkyl with 1 to 5 C-atoms, in particular methyl, ethyl or n-propyl, W<sup>4</sup>, W<sup>5</sup> and W<sup>6</sup> being independently of each other Cl, oxaalkyl or oxacarbonylalkyl with 1 to 5 C-atoms, Phe being 1,4-phenylene and k<sub>1</sub> and k<sub>2</sub> being independently of each other 0 or 1.

[0041] Especially preferred groups P are CH<sub>2</sub>=CH-COO-, CH<sub>2</sub>=C(CH<sub>3</sub>)-COO-, CH<sub>2</sub>=CH-, CH<sub>2</sub>=CH-O- and



[0042] Very preferred are acrylate and oxetane groups. Oxetanes produce less shrinkage upon polymerisation (cross-linking), which results in less stress development within films, leading to higher retention of ordering and fewer defects. Oxetane cross-linking also requires cationic initiator, which unlike free radical initiator is inert to oxygen.

[0043] As for the spacer group Sp all groups can be used that are known for this purpose to those skilled in the art. The spacer group Sp is preferably a linear or branched alkylene group having 1 to 20 C atoms, in particular 1 to 12 C atoms, in which, in addition, one or more non-adjacent CH<sub>2</sub> groups may be replaced by -O-, -S-, -NH-, -N(CH<sub>3</sub>)-, -CO-, -O-CO-, -S-CO-, -O-COO-, -CO-S-, -CO-O-, -CH(halogen)-, -C(halogen)<sub>2</sub>-, -CH(CN)-, -CH=CH- or -C≡C-, or a siloxane group.

[0044] Typical spacer groups are for example -(CH<sub>2</sub>)<sub>p</sub>-, -(CH<sub>2</sub>CH<sub>2</sub>O)<sub>r</sub>-CH<sub>2</sub>CH<sub>2</sub>-, -CH<sub>2</sub>CH<sub>2</sub>-S-CH<sub>2</sub>CH<sub>2</sub>- or -CH<sub>2</sub>CH<sub>2</sub>-NH-CH<sub>2</sub>CH<sub>2</sub>- or -(SiR<sup>0</sup>R<sup>00</sup>-O)<sub>p</sub>-, with p being an integer from 2 to 12, r being an integer from 1 to 3 and R<sup>0</sup> and R<sup>00</sup> having the meanings given in formula I.

[0045] Preferred spacer groups are ethylene, propylene, butylene, pentylene, hexylene, heptylene, octylene, nonylene, decylene, undecylene, dodecylene, octadecylene, ethyleneoxyethylene, methyleneoxybutylene, ethylene-thioethylene, ethylene-N-methyl-iminoethylene, 1-methylalkylene, ethenylene, propenylene and butenylene for example.

[0046] Further preferred are compounds with one or two groups P-Sp-X wherein Sp and/or X is a single bond.


[0047] In case of compounds with two groups P-Sp-X, each of the two polymerisable groups P, the two spacer groups Sp, and the two linkage groups X can be identical or different.

[0048] SCLCPs obtained from the inventive compounds or mixtures by polymerisation or copolymerisation have a backbone that is formed by the polymerisable group P in formula I.

[0049] The mono-, oligo- and polymers of the present invention can be synthesized according to or in analogy to known methods. Some preferred methods are described below.

[0050] Starting from the commercially available 3-bromobenzo[b]thiophene (5), a synthetic route to poly(2,2'-bisbenzo[b]thiophene) (4) is outlined below in Scheme 1. 3-bromobenzo[b]thiophene (5) is alkylated to (6) using an alkyl grignard and Ni(dppp)Cl<sub>2</sub>. Benzo[b]thiophene (6) is brominated at the 2-position using n-butyllithium followed by bromine to yield (7). 2-Bromobenzo[b]thiophene (7) is homo-coupled using a liganded nickel complex reducing agent (generated from NaH, t-AmONa, Ni(OAc)<sub>2</sub> and bipyridine) to yield 2,2'-bisbenzo[b]thiophene (2). Bromination of 2,2'-bisbenzo[b]thiophene (2) with N-bromosuccinimide or bromine water yields 5,5'-dibromo 2,2'-bisbenzo[b]thiophene (8).

[0051] Poly(2,2'-bisbenzo[b]thiophene) (4) is synthesised from 5,5'-dibromo-2,2'-bisbenzo[b]thiophene (8) by one of two methods. Firstly, (8) is directly polymerised using Ni(cod)<sub>2</sub> and triphenylphosphine (Yamamoto coupling) to yield (4) [see T. Yamamoto, A. Morita, Y. Miyazaki, T. Maruyama, H. Wakayama, Z. H. Zhou, Y. Nakamura, T. Kanbara, S. Sasaki and K. Kubota, *Macromolecules*, 1992, **25**, 1214]. Alternatively, (8) is converted to the mono-Grignard and polymerised using Ni(dppp)Cl<sub>2</sub> to yield (4) [see Loewe, R.S., S.M. Khersonsky, and R.D. McCullough, *Advanced Materials*, 1999, **11**(3), 250-253; Loewe, R.S., et al., *Macromolecules*, 2001, **34**, 4324-4337].


Scheme 1:Reactive mesogens

**[0052]** Compounds of formula I comprising polymerisable groups can be synthesized according to or in analogy to the following methods.

**[0053]** As shown in Scheme 2, 5,5'-dibromo-2,2'-bisbenzo[b]thiophene (**8**) can be cross-coupled with an alkyl zinc reagent in the presence of a nickel catalyst to yield (**9**) [see B. H. Lipshutz, P. A. Blomgren and S. K. Kim, *Tetrahedron Lett.*, 1999, **40**, 2, 197].

**[0054]** Many organozinc reagents are commercially available or are readily prepared from the corresponding alkyl iodide. Routine methodology converts the bis-alkyl alcohol or chloride (**9**) into the bis-acrylate or bis-oxetane.

Scheme 2:




wherein m is an integer e.g. from 1 to 20 and P is a protecting group.


[0055] Polymerisation of reactive mesogens can be carried out for example by thermal cross-linking or photoinitiated cross-linking.

Polymers containing conjugated groups  $\text{CX}^1=\text{CX}^2$  or Ar

[0056] The Stille coupling of dibromo 2,2'-bisbenzo[b]thiophene (8) with the bis-organotin reagent (10) as shown in Scheme 3 yields polymer (11) containing  $\text{CX}^1=\text{CX}^2$  groups [see R. S. Loewe and R. D. McCullough, *Chem. Mater.*, 2000, **12**, 3214.].


### Scheme 3





**[0057]** The Suzuki coupling of dibromo 2,2'-bisbenzo[b]thiophene (**8**) with bis-boronic acid (**12**) according to Scheme 4 yields polymer (**13**) containing aryl groups.


#### Scheme 4:



**[0058]** A route to poly(2,5-benzo[b]thiophene) (**3**) is outlined in scheme 5.

**[0059]** 3-Alkylbenzo[b]thiophene (**6**) is lithiated in the 2 position by treatment with n-BuLi, and the resulting anion is reacted with iodine to afford **14**. This intermediate is brominated in the 5 position by treatment with bromine to afford **15**. Subsequent lithiation at the more reactive iodo group followed by treatment with  $\text{MgBr}_2 \cdot \text{OEt}_2$  or  $\text{ZnCl}_2$  yields the organomagnesium or organozinc intermediate respectively. Addition of a nickel catalyst followed by warming affords polymer (**3**).

#### Scheme 5:



[0060] A further aspect of the invention relates to both the oxidised and reduced form of the compounds and materials according to this invention. Either loss or gain of electrons results in formation of a highly delocalised ionic form, which is of high conductivity. This can occur on exposure to common dopants. Suitable dopants and methods of doping are known to those skilled in the art, e.g. from EP 0 528 662, US 5,198,153 or WO 96/21659.

[0061] The doping process typically implies treatment of the semiconductor material with an oxidating or reducing agent in a redox reaction to form delocalised ionic centres in the material, with the corresponding counterions derived from the applied dopants. Suitable doping methods comprise for example exposure to a doping vapor in the atmospheric pressure or at a reduced pressure, electrochemical doping in a solution containing a dopant, bringing a dopant into contact with the semiconductor material to be thermally diffused, and ion-implantation of the dopant into the semiconductor material.

[0062] When electrons are used as carriers, suitable dopants are for example halogens (e.g.  $I_2$ ,  $Cl_2$ ,  $Br_2$ ,  $ICl$ ,  $ICl_3$ ,  $IBr$  and  $IF$ ), Lewis acids (e.g.  $PF_5$ ,  $AsF_5$ ,  $SbF_5$ ,  $BF_3$ ,  $BCl_3$ ,  $SbCl_5$ ,  $BBr_3$  and  $SO_3$ ), protonic acids, organic acids, or amino acids (e.g.  $HF$ ,  $HCl$ ,  $HNO_3$ ,  $H_2SO_4$ ,  $HClO_4$ ,  $FSO_3H$  and  $ClSO_3H$ ), transition metal compounds (e.g.  $FeCl_3$ ,  $FeOCl$ ,  $Fe(ClO_4)_3$ ,  $Fe(4-CH_3C_6H_4SO_3)_3$ ,  $TiCl_4$ ,  $ZrCl_4$ ,  $HfCl_4$ ,  $NbF_5$ ,  $NbCl_5$ ,  $TaCl_5$ ,  $MoF_5$ ,  $MoCl_5$ ,  $WF_6$ ,  $WCl_6$ ,  $UF_6$  and  $LnCl_3$  (wherein  $Ln$  is a lanthanoid), anions (e.g.  $Cl^-$ ,  $Br^-$ ,  $I^-$ ,  $I_3^-$ ,  $HSO_4^-$ ,  $SO_4^{2-}$ ,  $NO_3^-$ ,  $ClO_4^-$ ,  $BF_4^-$ ,  $PF_6^-$ ,  $AsF_6^-$ ,  $SbF_6^-$ ,  $FeCl_4^-$ ,  $Fe(CN)_6^{3-}$ , and anions of various sulfonic acids, such as  $aryl-SO_3^-$ ). When holes are used as carriers, examples of dopants are cations (e.g.  $H^+$ ,  $Li^+$ ,  $Na^+$ ,  $K^+$ ,  $Rb^+$  and  $Cs^+$ ), alkali metals (e.g.,  $Li$ ,  $Na$ ,  $K$ ,  $Rb$ , and  $Cs$ ), alkaline-earth metals (e.g.,  $Ca$ ,  $Sr$ , and  $Br$ ),  $O_2$ ,  $XeOF_4$ ,  $(NO_2^+)(SbF_6^-)$ ,  $(NO_2^+)(SbCl_6^-)$ ,  $(NO_2^+)(BF_4^-)$ ,  $AgClO_4$ ,  $H_2IrCl_6$ ,  $La(NO_3)_3 \cdot 6H_2O$ ,  $FSO_2OOSO_2F$ ,  $Eu$ , acetylcholine,  $R_4N^+$  ( $R$  is an alkyl group),  $R_4P^+$  ( $R$  is an alkyl group),  $R_6As^+$  ( $R$  is an alkyl group), and  $R_3S^+$  ( $R$  is an alkyl group).

[0063] The conducting form of the compounds and materials of the present invention can be used as an organic "metal" in applications, for example, but not limited to, charge injection layers and ITO planarising layers in organic light emitting diode applications, films for flat panel displays and touch screens, antistatic films, printed conductive substrates, patterns or tracts in electronic applications such as printed circuit boards and condensers.

[0064] A preferred embodiment of the present invention relates to mono-, oligo- and polymers of formula I that are mesogenic or liquid crystalline, and very preferably comprise one or more polymerisable groups. Very preferred materials of this type are monomers and oligomers of formula I wherein  $n$  is an integer from 1 to 15 and  $R^1$  and/or  $R^2$  denote P-Sp-X.

[0065] These materials are particularly useful as semiconductors or charge transport materials, as they can be aligned into uniform highly ordered orientation in their liquid crystal phase by known techniques, thus exhibiting a higher degree of order that leads to particularly high charge carrier mobility. The highly ordered liquid crystal state can be fixed by in situ polymerisation or crosslinking via the groups P to yield polymer films with high charge carrier mobility and high thermal, mechanical and chemical stability.

[0066] It is also possible to copolymerise the polymerisable mono-, oligo- and polymers according to the present invention with other polymerisable mesogenic or liquid crystal monomers that are known from prior art, in order to induce or enhance liquid crystal phase behaviour.

[0067] Thus, another object of the invention is a polymerisable liquid crystal material comprising one or more mono-, oligo- or polymers of the present invention as described above and below comprising at least one polymerisable group, and optionally comprising one or more further polymerisable compounds, wherein at least one of the polymerisable mono-, oligo- and polymers of the present invention and/or the further polymerisable compounds is mesogenic or liquid crystalline.

**[0068]** Particularly preferred are liquid crystal materials having a nematic and/or smectic phase. For FET applications smectic materials are especially preferred. For OLED applications nematic or smectic materials are especially preferred.

**[0069]** Another object of the present invention is an anisotropic polymer film with charge transport properties obtainable from a polymerisable liquid crystal material as defined above that is aligned in its liquid crystal phase into macroscopically uniform orientation and polymerised or crosslinked to fix the oriented state.

**[0070]** Another object of the invention is a liquid crystal side chain polymer (SCLCP) obtained from a polymerisable liquid crystal material as defined above by polymerisation or polymeranalogous reaction. Particularly preferred are SCLCPs obtained from one or more monomers according to formula I wherein one or both of  $R^1$  and  $R^2$  are a polymerisable or reactive group, or from a polymerisable mixture comprising one or more of such monomers of formula I.

**[0071]** Another object of the invention is an SCLCP obtained from one or more monomers of formula I wherein one or both of  $R^1$  and  $R^2$  are a polymerisable group, or from a polymerisable liquid crystal mixture as defined above, by copolymerisation or polymeranalogous reaction together with one or more additional mesogenic or non-mesogenic comonomers.

**[0072]** Side chain liquid crystal polymers or copolymers (SCLCPs), in which the semiconducting component is located as a pendant group, separated from a flexible backbone by an aliphatic spacer group, offer the possibility to obtain a highly ordered lamellar like morphology. This structure consists of closely packed conjugated aromatic mesogens, in which very close (typically  $< 4 \text{ \AA}$ ) pi-pi stacking can occur. This stacking allows intermolecular charge transport to occur more easily, leading to high charge carrier mobilities. SCLCPs are advantageous for specific applications as they can be readily synthesized before processing and then e.g. be processed from solution in an organic solvent. If SCLCPs are used in solutions, they can orient spontaneously when coated onto an appropriate surface and when at their mesophase temperature, which can result in large area, highly ordered domains.

**[0073]** Polymerisation is preferably carried out by in-situ polymerisation of a coated layer of the material, preferably during fabrication of the electronic or optical device comprising the inventive semiconductor material. In case of liquid crystal materials, these are preferably aligned in their liquid crystal state into homeotropic orientation prior to polymerisation, where the conjugated pi-electron systems are orthogonal to the direction of charge transport. This ensures that the intermolecular distances are minimised and hence then energy required to transport charge between molecules is minimised. The molecules are then polymerised or crosslinked to fix the uniform orientation of the liquid crystal state. Alignment and curing are carried out in the liquid crystal phase or mesophase of the material. This technique is known in the art and is generally described for example in D.J. Broer, et al., *Angew. Makromol. Chem.* 183, (1990), 45-66

**[0074]** Alignment of the liquid crystal material can be achieved for example by treatment of the substrate onto which the material is coated, by shearing the material during or after coating, by application of a magnetic or electric field to the coated material, or by the addition of surface-active compounds to the liquid crystal material. Reviews of alignment techniques are given for example by I. Sage in "Thermotropic Liquid Crystals", edited by G. W. Gray, John Wiley & Sons, 1987, pages 75-77, and by T. Uchida and H. Seki in "Liquid Crystals - Applications and Uses Vol. 3", edited by B. Bahadur, World Scientific Publishing, Singapore 1992, pages 1-63. A review of alignment materials and techniques is given by J. Cognard, *Mol. Cryst. Liq. Cryst.* 78, Supplement 1 (1981), pages 1-77.

**[0075]** Polymerisation takes place by exposure to heat or actinic radiation. Actinic radiation means irradiation with light, like UV light, IR light or visible light, irradiation with X-rays or gamma rays or irradiation with high energy particles, such as ions or electrons. Preferably polymerisation is carried out by UV irradiation at a non-absorbing wavelength. As a source for actinic radiation for example a single UV lamp or a set of UV lamps can be used. When using a high lamp power the curing time can be reduced. Another possible source for actinic radiation is a laser, like e.g. a UV laser, an IR laser or a visible laser.

**[0076]** Polymerisation is preferably carried out in the presence of an initiator absorbing at the wavelength of the actinic radiation. For example, when polymerising by means of UV light, a photoinitiator can be used that decomposes under UV irradiation to produce free radicals or ions that start the polymerisation reaction. When curing polymerisable materials with acrylate or methacrylate groups, preferably a radical photoinitiator is used, when curing polymerisable materials with vinyl, epoxide and oxetane groups, preferably a cationic photoinitiator is used. It is also possible to use a polymerisation initiator that decomposes when heated to produce free radicals or ions that start the polymerisation. As a photoinitiator for radical polymerisation for example the commercially available Irgacure 651, Irgacure 184, Darocure 1173 or Darocure 4205 (all from Ciba Geigy AG) can be used, whereas in case of cationic photopolymerisation the commercially available UVI 6974 (Union Carbide) can be used.

**[0077]** The polymerisable material can additionally comprise one or more other suitable components such as, for example, catalysts, sensitizers, stabilizers, inhibitors, chain-transfer agents, co-reacting monomers, surface-active compounds, lubricating agents, wetting agents, dispersing agents, hydrophobing agents, adhesive agents, flow improvers, defoaming agents, deaerators, diluents, reactive diluents, auxiliaries, colourants, dyes or pigments.

**[0078]** Mono-, oligo- and polymers comprising one or more groups P-Sp-X can also be copolymerised with polymerisable mesogenic compounds to induce, or, in case of mesogenic materials of formula I, enhance liquid crystal phase

behaviour. Polymerisable mesogenic compounds that are suitable as comonomers are known in prior art and disclosed for example in WO 93/22397; EP 0,261,712; DE 195,04,224; WO 95/22586 and WO 97/00600.

**[0079]** SCLCPs can be prepared from the polymerisable compounds or mixtures according to the invention by the methods described above, or by conventional polymerisation techniques which are known to those skilled in the art, including for example radicalic, anionic or cationic chain polymerisation, polyaddition or polycondensation. Polymerisation can be carried out for example as polymerisation in solution, without the need of coating and prior alignment, or polymerisation in situ. It is also possible to form SCLCPs by grafting compounds according to the invention with a suitable reactive group, or mixtures thereof, to presynthesized isotropic or anisotropic polymer backbones in a polymeranalogous reaction. For example, compounds with a terminal hydroxy group can be attached to polymer backbones with lateral carboxylic acid or ester groups, compounds with terminal isocyanate groups can be added to backbones with free hydroxy groups, compounds with terminal vinyl or vinyloxy groups can be added e.g. to polysiloxane backbones with Si-H groups. It is also possible to form SCLCPs by copolymerisation or polymeranalogous reaction from the inventive compounds together with conventional mesogenic or non mesogenic comonomers. Suitable comonomers are known to those skilled in the art. In principle it is possible to use all conventional comonomers known in the art that carry a reactive or polymerisable group capable of undergoing the desired polymer-forming reaction, like for example a polymerisable or reactive group P as defined above. Typical mesogenic comonomers are for example those mentioned in WO 93/22397; EP 0,261,712; DE 195,04,224; WO 95/22586 and WO 97/00600. Typical non mesogenic comonomers are for example alkyl mono- or diacrylates or alkyl mono- or dimethacrylates with alkyl groups of 1 to 20 C atoms, like methyl acrylate or methyl methacrylate, trimethylpropane trimethacrylate or pentaerythritol tetraacrylate.

**[0080]** The mono-, oligo- and polymers of the present invention are useful as optical, electronic and semiconductor materials, in particular as charge transport materials in field effect transistors (FETs) e.g. as components of integrated circuitry, ID tags or TFT applications. Alternatively, they may be used in organic light emitting diodes (OLEDs) in electroluminescent display applications or as backlight of e.g. liquid crystal displays, as photovoltaics or sensor materials, for electrophotographic recording, and for other semiconductor applications.

**[0081]** Especially the oligomers and polymers according to the invention show advantageous solubility properties which allow production processes using solutions of these compounds. Thus films, including layers and coatings, may be generated by low cost production techniques e.g. spin coating. Suitable solvents or solvent mixtures comprise alkanes and/ or aromatics, especially their fluorinated derivatives.

**[0082]** The materials of the present invention are useful as optical, electronic and semiconductor materials, in particular as charge transport materials in field effect transistors (FETs), as photovoltaics or sensor materials, for electrophotographic recording, and for other semiconductor applications. Such FETs, where an organic semiconductive material is arranged as a film between a gate-dielectric and a drain and a source electrode, are generally known e.g. from US 5,892,244; WO 00/79617, US 5,998,804, and from the references cited in the background and prior art chapter and listed below. Due to the advantages, like low cost production using the solubility properties of the compounds according to the invention and thus the processibility of large surfaces, preferred applications of these FETs are such as integrated circuitry, TFT-displays and security applications.

**[0083]** In security applications, field effect transistors and other devices with semiconductive materials, like transistors or diodes, may be used for ID tags or security markings to authenticate and prevent counterfeiting of documents of value like banknotes, credit cards or ID cards, national ID documents, licenses or any product with money value, like stamps, tickets, shares, cheques etc..


**[0084]** Alternatively, the mono-, oligo- and polymers according to the invention may be used in organic light emitting devices or diodes (OLEDs), e.g. in display applications or as backlight of e.g. liquid crystal displays. Common OLEDs are realized using multilayer structures. An emission layer is generally sandwiched between one or more electron-transport and/ or hole-transport layers. By applying an electric voltage electrons and holes as charge carriers move towards the emission layer where their recombination leads to the excitation and hence luminescence of the lumophor units contained in the emission layer. The inventive compounds, materials and films may be employed in one or more of the charge transport layers and/or in the emission layer, corresponding to their electrical and/ or optical properties. Furthermore their use within the emission layer is especially advantageous, if the compounds, materials and films according to the invention show electroluminescent properties themselves or comprise electroluminescent groups or compounds. The selection, characterization as well as the processing of suitable monomeric, oligomeric and polymeric compounds or materials for the use in OLEDs is generally known by a person skilled in the art, see e. g. Meerholz, Synthetic Materials, 111-112, 2000, 31-34, Alcalá, J. Appl. Phys., 88, 2000, 7124-7128 and the literature cited therein.

**[0085]** According to another use, the inventive compounds, materials or films, especially those which show photoluminescent properties, may be employed as materials of light sources, e.g. of display devices such as described in EP 0 889 350 A1 or by C. Weder et al., Science, 279, 1998, 835-837.



## Claims

## 1. Mono-, oligo- and polymers of formula I



wherein

A and C are independently of each other  $-CX^1= CX^2-$ ,  $-C\equiv C-$ , or optionally substituted arylene or heteroarylene,

$X^1$  and  $X^2$  are independently of each other H, F, Cl or CN,

B is 2,5-benzo[b]thiophene or 2,2'-bisbenzo[b]thiophene that is optionally substituted with one or more groups R,

R is H, halogen, straight chain, branched or cyclic alkyl with 1 to 20 C-atoms, which may be unsubstituted, mono- or poly-substituted by F, Cl, Br, I or CN, it being also possible for one or more non-adjacent  $CH_2$  groups to be replaced, in each case independently from one another, by  $-O-$ ,  $-S-$ ,  $-NH-$ ,  $-NR^0-$ ,  $-SiR^0R^{00}-$ ,  $-SnR^0R^{00}-$ ,  $-CO-$ ,  $-COO-$ ,  $-OCO-$ ,  $-OCO-O-$ ,  $-S-CO-$ ,  $-CO-S-$ ,  $-CH=CH-$  or  $-C\equiv C-$  in such a manner that O and/or S atoms are not linked directly to one another, optionally substituted aryl or heteroaryl, or P-Sp-X,

$R^1$  and  $R^2$  have independently of each other one of the meanings of R,

$R^0$ ,  $R^{00}$  are independently of each other H or alkyl with 1 to 12 C-atoms,

P is a polymerisable or reactive group,

Sp is a spacer group or a single bond, and


X is  $-O-$ ,  $-S-$ ,  $-OCH_2-$ ,  $-CH_2O-$ ,  $-CO-$ ,  $-COO-$ ,  $-OCO-$ ,  $-OCO-O-$ ,  $-CO-NR^0-$ ,  $-NR^0-CO-$ ,  $-OCH_2-$ ,  $-CH_2O-$ ,  $-SCH_2-$ ,  $-CH_2S-$ ,  $-CH=CH-COO-$ ,  $-OOC-CH=CH-$  or a single bond,

a, b, c are independently of each other 0 or 1, with  $a + b + c > 0$ , and wherein in at least one recurring unit  $[(A)_a-(B)_b-(C)_c]$  b is 1, and


n is an integer  $\geq 1$ ,

wherein the recurring units  $[(A)_a-(B)_b-(C)_c]$  can be identical or different, with the proviso that in case n is 1 and a and c are 0, at least one of R,  $R^1$  and  $R^2$  is P-Sp-X.

## 2. Mono-, oligo- and polymers according to claim 1, wherein B is selected of the following formulae




IIa



IIb


wherein  $R^3$  to  $R^{10}$  independently of each other have one of the meanings of R in formula I.

3. Mono-, oligo- and polymers according to claim 1 or 2, wherein n is an integer from 1 to 5000.
4. Mono-, oligo- and polymers according to at least one of claims 1 to 3, wherein  $R^3$  to  $R^{10}$  are independently of each other selected from  $C_1$ - $C_{20}$ -alkyl that is optionally substituted with one or more fluorine atoms,  $C_1$ - $C_{20}$ -alkenyl,  $C_1$ - $C_{20}$ -alkynyl,  $C_1$ - $C_{20}$ -alkoxy,  $C_1$ - $C_{20}$ -thioether,  $C_1$ - $C_{20}$ -silyl,  $C_1$ - $C_{20}$ -ester,  $C_1$ - $C_{20}$ -amino,  $C_1$ - $C_{20}$ -fluoroalkyl, or optionally substituted aryl or heteroaryl.
5. Mono-, oligo- and polymers according to claim 4, wherein  $R^3$  and  $R^4$  are independently of each other selected from  $C_1$ - $C_{20}$ -alkyl that is optionally substituted with one or more fluorine atoms,  $C_1$ - $C_{20}$ -alkenyl,  $C_1$ - $C_{20}$ -alkynyl,  $C_1$ - $C_{20}$ -alkoxy,  $C_1$ - $C_{20}$ -thioether,  $C_1$ - $C_{20}$ -silyl,  $C_1$ - $C_{20}$ -ester,  $C_1$ - $C_{20}$ -amino,  $C_1$ - $C_{20}$ -fluoroalkyl, or optionally substituted aryl or heteroaryl, and  $R^5$  to  $R^{10}$  are H.
6. Mono-, oligo- and polymers according to at least one of claims 1 to 5, wherein n is an integer from 1 to 15 and one or both of  $R^1$  and  $R^2$  denote P-Sp-X.
7. Oligo- and polymers according to at least one of claims 1 to 6, wherein n is an integer from 2 to 5000.
8. Mono-, oligo- and polymers according to at least one of claims 1 to 7, wherein P is selected from  $CH_2=CW^1-COO-$ ,




$CH_2=CW^2-(O)_{k1}-$ ,  $CH_3-CH=CH-O-$ ,  $HO-CW^2W^3-$ ,  $HS-CW^2W^3-$ ,  $HW^2N-$ ,  $HO-CW^2W^3-NH-$ ,  $CH_2=CW^1-CO-NH-$ ,  $CH_2=CH-(COO)_{k1}-Phe-(O)_{k2}-$ ,  $Phe-CH=CH-$ ,  $HOOC-$ ,  $OCN-$  and  $W^4W^5W^6Si-$ , with  $W^1$  being H, Cl, CN, phenyl or alkyl with 1 to 5 C-atoms, in particular H, Cl or  $CH_3$ ,  $W^2$  and  $W^3$  being independently of each other H or alkyl with 1 to 5 C-atoms, in particular methyl, ethyl or n-propyl,  $W^4$ ,  $W^5$  and  $W^6$  being independently of each other Cl, oxalkyl or oxacarbonylalkyl with 1 to 5 C-atoms, Phe being 1,4-phenylene and  $k_1$  and  $k_2$  being independently of each other 0 or 1.


9. Mono-, oligo- and polymers according to at least one of claims 1 to 8, selected from the following formulae




Ia







Ib







Ic



Id





wherein  $R^1$  to  $R^{10}$  have independently of each other one of the meanings of  $R$  in formula I,  $Ar$  is arylene or heteroarylene, and  $n$  is an integer from 1 to 5000.

- 50
10. Polymerisable liquid crystal material comprising one or more mono-, oligo- or polymers of at least one of claims 1 to 9 comprising at least one polymerisable group, and optionally comprising one or more further polymerisable compounds, wherein at least one of the polymerisable mono-, oligo- and polymers of claims 1 to 9 and/or the further polymerisable compounds is mesogenic or liquid crystalline.
- 55
11. Anisotropic polymer film with charge transport properties obtainable from a polymerisable liquid crystal material according to claim 10 that is aligned in its liquid crystal phase into macroscopically uniform orientation and polymerised or crosslinked to fix the oriented state.

12. Side chain liquid crystal polymer obtained by polymerisation of one or more mono- or oligomers or a polymerisable material according to claims 1 to 10 or by grafting one or more mono- or oligomers or a polymerisable material according to claims 1 to 10 to a polymer backbone in a polymeranalogous reaction, optionally with one or more additional mesogenic or non-mesogenic comonomers.

13. Use of the mono-, oligo- and polymers, polymerisable material and polymer of claims 1 to 12 as semiconductors or charge transport materials, in particular in optical, electrooptical or electronic devices, like for example components of integrated circuitry, field effect transistors (FET) for example as thin film transistors in flat panel display applications or for Radio Frequency Identification (RFID) tags, or in semiconducting components for organic light emitting diode (OLED) applications such as electroluminescent displays or backlights of e.g. liquid crystal displays, for photovoltaic or sensor devices, as electrode materials in batteries, as photoconductors and for electrophotographic applications like electrophotographic recording.

14. Field effect transistor, for example as a component of integrated circuitry, as a thin film transistor in flat panel display applications, or in a Radio Frequency Identification (RFID) tag, comprising one or more mono-, oligo- or polymers according to the invention comprising one or more mono-, oligo- or polymers, polymerisable material or polymer of claims 1 to 12.

15. Security marking or device comprising comprising one or more mono-, oligo- or polymers, a polymerisable material or a polymer of claims 1 to 12, or a FET or RFID tag according to claim 14.

16. Mono-, oligo- and polymers, a material or polymer according to at least one of claims 1 to 12, which are oxidatively or reductively doped to form conducting ionic species.

17. Charge injection layer, planarising layer, antistatic film or conducting substrate or pattern for electronic applications or flat panel displays, comprising mono-, oligo- or polymers, a material or polymer according to claim 16.



European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number  
EP 02 01 9693

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
P,X	EP 1 138 713 A (SHARP KK) 4 October 2001 (2001-10-04) * claim 1 *	1-5,7, 9-17	C08G61/12 C07D333/52
X,D	WANG ET. ALL: "Electrochemical Polymerization of thianaphthene" JOURNAL OF ELECTROANALYTICAL CHEMISTRY, no. 510, 2001, pages 29-34, XP002218117 * page 32; figure 5 *	1,2,9	
X	KIEBOOMS R ET AL: "SYNTHESIS, ELECTRICAL, AND OPTICAL PROPERTIES OF CONJUGATED POLYMERS", HANDBOOK OF ADVANCED ELECTRONIC AND PHOTONIC MATERIALS AND DEVICES, XX, XX, VOL. 8, PAGE(S) 1-102 XP001029240 * page 24; figure 51 *	1,2,9	
X	SHTAREV ET AL: "Synthesis of Conjugated F-Polyenes Containing Thienyl Ring Systems" JOURNAL OF ORGANIC CHEMISTRY, AMERICAN CHEMICAL SOCIETY, EASTON, US, vol. 62, 1997, pages 5608-5614, XP002153296 ISSN: 0022-3263 *** scheme 2,3, compound 1f *** --- -/--	1	TECHNICAL FIELDS SEARCHED (Int.Cl.7)  C08G C07D
The present search report has been drawn up for all claims			
Place of search <b>THE HAGUE</b>		Date of completion of the search <b>24 October 2002</b>	Examiner <b>Paalman, R</b>
<p><b>CATEGORY OF CITED DOCUMENTS</b></p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons &amp; : member of the same patent family, corresponding document</p>			

EPO FORM 1533-33-32 (PC/C01)



European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number  
EP 02 01 9693

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	SAKANISHI K ET AL: "Selective dimerization of benzothiophene using supported aluminum sulfate under supercritical CO2 conditions" JOURNAL OF SUPERCRITICAL FLUIDS, PRA PRESS, US, vol. 13, no. 1-3, 15 June 1998 (1998-06-15), pages 203-210, XP004264876 ISSN: 0896-8446 * page 209; figure 8 *	1	
X,D	AN H., SEKI M., YOYMIYA R. : "Electrochemical polymerization of benzo(b)thiophene and electrical properties of poly(benzo(b)thiophene)" MAKROMOL. CHEM., RAPID COMMUNICATION, no. 8, 1987, pages 325-329, XP002218118 * page 325; figure 1 *	1	
The present search report has been drawn up for all claims			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
Place of search <b>THE HAGUE</b>		Date of completion of the search <b>24 October 2002</b>	Examiner <b>Paalman, R</b>
<b>CATEGORY OF CITED DOCUMENTS</b> X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

EPO FORM 1503 03 02 (P44C01)



ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.

EP 02 01 9693

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.  
The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

24-10-2002

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 1138713 A	04-10-2001	GB 2360776 A	03-10-2001
		EP 1138713 A2	04-10-2001
		JP 2001335622 A	04-12-2001
		US 2002041976 A1	11-04-2002
<hr/>			

EPO FORM P0455

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**THIS PAGE BLANK (USPTO)**

# EUROPEAN PATENT OFFICE

## Patent Abstracts of Japan

PUBLICATION NUMBER : 03038588  
PUBLICATION DATE : 19-02-91



APPLICATION DATE : 03-07-89  
APPLICATION NUMBER : 01171721

APPLICANT : DAISO CO LTD;

INVENTOR : MIYAMOTO KYUICHI;

INT.CL. : C07D495/22 C08G 61/12 C09K 3/00

TITLE : THIOPHENE DERIVATIVE, COMPLEX  
CONTAINING THE DERIVATIVE AS  
COMPONENT AND ITS PRODUCTION



ABSTRACT : NEW MATERIAL:3,4:3',4'-Bithieno[2,3-b]thiophene of formula I.

USE: An electron donor constituting a charge transfer complex. Electrolytic polymerization of the compound gives a polymer having high electrical conductivity.

PREPARATION: The objective compound can be produced by reacting 3,4-dibromothiophene with a bis (-triphenylphosphine)nickel (n) II halide [e. g. bis(triphenylphosphine)nickel(II) chloride], zinc and a tetraalkyl ammonium halide (e. g. tetramethyl ammonium chloride) in a solvent (e.g. pentane or benzene) preferably at 20-130° for 0.5-50hr.

COPYRIGHT: (C)1991,JPO&Japio

**THIS PAGE BLANK (USPTO)**